

IN THE ABSTRACT

Please amend the Abstract as follows:

--A method for producing a ferrule having a plurality of fiber holes for insertion of optical fibers formed between two pin holes for insertion of guide ~~pings~~ pins, and a ferrule produced by the method. The method comprises a step of injecting a synthetic resin in a mold for forming the ferrule while holding a plurality of pins with a Young's modulus of (22 to 59) $\times 10^{10}$ N/m² for forming the fiber holes at two points separated by a distance of 1.5 to 4 mm in a lengthwise direction of the pins.--